



CHAPCO® ADDITIVE

Acrylic Latex Patch Additive



PRODUCT DATA

SURFACE PREPARATION

1. PRODUCT NAME

CHAPCO® ADDITIVE Acrylic Latex Patch Additive

2. MANUFACTURER

H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504-6451 U.S.A.
800-552-6225 Office
www.chapco-adhesive.com

3. DESCRIPTION

CHAPCO ADDITIVE Acrylic Latex Patch Additive is recommended for use as an admixture for selected CHAPCO brand floor preparation products, especially when used as an embossing leveler. It is designed to improve adhesive, bond and flexural strengths.

Key Benefits and Features

- Acrylic latex based
- Freeze/thaw stable
- Increases adhesion
- Enhances flexural strength
- Highly water resistant when cured

Packaging

One U.S. gallon jug 8.6 lbs (3.9 kg)
Product #33-1512-5069

Recommended Substrates

Refer to the appropriate product package or product data sheet of CHAPCO SmoothFinish™, CHAPCO PATCH or CHAPCO QPD PLUS.

Storage/Shelf Life

Store in a cool dry area away from direct sunlight. Maximum shelf life is 18 months from date of manufacture in unopened container.

Limitations

Do not use in areas subject to hydrostatic pressure. Not for use as a sealer or a primer.

Cautions

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about guidelines for the proper use and application of the covered CHAPCO products under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

CHAPCO ADDITIVE Acrylic Latex Patch Additive	
Physical State	Liquid: Acrylic Latex
Color	White
Odor	Mild
Viscosity	Thin, pourable
VOC	12 grams/liter, less water
Wt. per U.S. Gallon	8.6 lbs. ± 0.1 lb.
Wt. per Liter	1.03 kg. ± 0.01 kg
Freeze/Thaw	Freeze/thaw stable. If frozen, thaw and stir before using.

5. INSTALLATION INSTRUCTIONS

Preparation of Surfaces

Refer to the appropriate product package or product data sheet of CHAPCO SmoothFinish, CHAPCO PATCH or CHAPCO QPD PLUS.

Mixing Instructions

For best results, room and product should be kept at 50°-70°F (10°- 21°C) for 24 hours before, during and 48 hours after installation. Add powder to liquid for ease of mixing. Avoid breathing dust and contact with eyes and skin. Refer to complete information on appropriate surface prep product package.

Application Instructions

For applications with CHAPCO SmoothFinish: Slowly add the entire bag of CHAPCO SmoothFinish into 2½ quarts of CHAPCO ADDITIVE mixing at a low speed (not exceeding 300 rpm to prevent entraining air). Mix thoroughly to a smooth, lump-free consistency. Apply as directed on the CHAPCO SmoothFinish data sheet.

For applications with CHAPCO PATCH: Slowly add the entire bag of CHAPCO Patch into 1 gallon of CHAPCO ADDITIVE mixing at a low speed (not exceeding 300 rpm to prevent entraining air). Mix thoroughly to a smooth, lump-free consistency. Apply as directed on the CHAPCO PATCH data sheet.

For applications with CHAPCO QPD PLUS: Slowly add the entire bag of CHAPCO QPD PLUS into 2½ quarts of CHAPCO ADDITIVE mixing at a low speed (not exceeding 300 rpm to prevent entraining air). Mix thoroughly to a smooth, lump-free consistency. Apply as directed on the CHAPCO QPD PLUS data sheet.

Clean-up

Wash tools, hands and equipment with warm soapy water while material is still fresh.

6. AVAILABILITY AND COST

To locate a distributor in your area, please contact:

phone: 800-832-9002
website: www.chapco-adhesive.com

7. WARRANTY

H.B. Fuller Construction Products Inc. offers a limited warranty on this product when installed in accordance with H.B. Fuller Construction Products Inc. printed specifications. Ask your sales associate or call 800-832-9002 for a copy of the limited warranty.

8. MAINTENANCE

Not applicable.

9. TECHNICAL ASSISTANCE

Information is available by calling the Technical Support Hotline:

Toll-free: 800-832-9023

Technical and Safety Literature:

To acquire technical and safety literature, please call 800-832-9023

10. FILING SYSTEM

Division 3 - Concrete
Division 9 - Finishes



H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504
PH 800.832.9002
www.chapco-adhesive.com