



CHAPCO® ROLLFAST™

Vinyl Flooring Adhesive

PRODUCT DATA

1. PRODUCT NAME

CHAPCO® RollFast™ Vinyl Flooring Adhesive 776



2. MANUFACTURER

H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504-6451 U.S.A.
800.552.6225 Office
800.952.2368 Fax
chapco-adhesive.com

3. DESCRIPTION

CHAPCO® RollFast™ Vinyl Flooring Adhesive allows you ease of use, to roll through flooring installations fast and effectively. This breakthrough, user-friendly adhesive is ideal for vinyl tile, vinyl plank and solid vinyl sheetgoods. This unique formulation dries quickly, has excellent resistance to moisture and alkali, provides a long open time, is easy to clean up and low-odor.

Product Features

- Ideal for LVT, LVP and solid vinyl heterogeneous or homogeneous sheetgoods
- Roller-applied adhesive allows installer to roll the adhesive onto the substrate efficiently
- Fast drying; accepts flooring in 10-15 minutes
- Moisture and alkali resistant up to 90% RH / 10 lbs. MVER and 7-11 pH
- Extended open time (6-8 hours)
- Heat weld after 60 minutes
- Solvent free and low VOC (VOC <1 g/L)
- LEED® Compliant and CRI Green Label Plus Certified

Packaging

Four U.S. Gallon plastic pail (15.13 L)
Product #7188701369

One U.S. Gallon plastic jug (3.78 L)
Product #7188705069

Coverage

Coverage will vary with the absorption rate (porosity) and surface profile of the substrate. With just one coat of RollFast™ Vinyl Flooring Adhesive, you can lay down the amount of adhesive needed for the specific vinyl flooring being installed. Figures below are presented only as guidelines.

Recommended Roller Size	Approximate Coverage
1/4" Nap	350-450 ft ² /US Gallon (35,6-37,2 m ² /3,78L)
3/8" Nap*	300-350 ft ² /US Gallon (28-35,6 m ² /3,78L)

* For stiff, heavy vinyl flooring a 3/8" Nap Roller may be required (for more information contact Technical Services).

Storage/Shelf Life

Store at a moderate room temperature.
Protect adhesive from freezing.
Refer to the Technical Data section of this PDS, for more information.

Limitations

- Although adhesive may be used when ambient or surface temperatures are between 60°F-90°F (16°C-32°C), always follow flooring manufacturer's temperature and installation guidelines for the vinyl flooring being installed.
- Always protect newly-installed vinyl flooring from heavy traffic, rolling loads, appliance or furniture placement for 24 hours after flooring installation.
- Do not use with fiberglass-backed vinyl sheetgoods, nor directly over peel and stick tile.
- Not for use in areas subject to flooding or water immersion.

- Do not use in coolers, freezers or seasonally used buildings subject to temperature or humidity extremes.
- Not recommended for use with felt-backed or mineral-backed vinyl sheetgoods, linoleum or rubber.
- Not recommended for use on stairs or vertical surfaces.
- May be used over in-floor heating systems, with a maximum floor temperature of 85°F, if allowed by the flooring manufacturer.
- Not for exterior use. Interior use only.

Cautions

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about guidelines for the proper use and application of the covered CHAPCO® brand products under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

CHAPCO® RollFast™ Vinyl Flooring Adhesive 776	
Base	Polymer latex
Physical State	Thin paste
Color	Off white
Open Time	6-8 hours depending on substrate porosity.
Weight per Gallon	8.7 lbs./gallon
VOC/Liter of Material	<1 gram (calculated)
Freeze/Thaw Stability	Stable for 3 cycles at 10°F (-12°C).
Storage	For optimal shelf life, store at a moderate room temperature, in closed containers, and protect this adhesive from freezing. If frozen, allow to return to room temperature slowly and stir before use. Avoid prolonged or repeated freeze thaw cycles.
Shelf Life	Maximum of 1 year from date of manufacture, in unopened container.

5. INSTALLATION INSTRUCTIONS

Suitable Substrates

When properly prepared, suitable substrates include:

- Concrete (all grade levels)
- Underlayment grade plywood
- Gypsum substrates (properly prepared)

Preparation of Surfaces

Floor must be clean, smooth, dry, and free of any foreign matter that would interfere with a good bond. Existing adhesive must be removed by mechanical means, such as shot blasting or scarification. Do not use solvents or liquid adhesive removers. Fill all cracks and depressions with a suitable CHAPCO® cement-based floor patch and/or underlayment. Best practices for cleaning typically include vacuuming and damp mopping.

Moisture Test: Concrete moisture testing must be performed in accordance to ASTM F1869 with levels not to exceed 10 lbs./1000 ft²/24 hrs. (3.63 kg/93 m² /24 hrs.) and/or ASTM F2170 with levels not to exceed 90%. **NOTE:** High moisture levels must be related to newly poured slabs with a functional moisture vapor barrier in place, and declining RH values.

For concrete with a prior history of uncorrected moisture conditions or problems involving higher moisture levels, treat the concrete with one of the following CHAPCO® brand



moisture mitigation solutions:

CHAPCO'S Defender™ - apply per PDS instructions and allow to cure. Once cured, apply CHAPCO® MP Multi-Purpose Primer followed by application of a minimum 1/8" thickness of the appropriate CHAPCO® cementitious floor patch. If thicker cementitious smoothing and leveling is needed, install a CHAPCO® self-leveling underlayment over the primed CHAPCO'S Defender™. If the concrete is smooth and level enough to accept vinyl flooring and does not require a cementitious underlayment, RollFast™ Vinyl Flooring Adhesive may be applied directly to the cured, primed CHAPCO'S Defender™ surface.

CHAPCO® Defender EZ™ - apply per PDS instructions and allow to dry. Apply a minimum 1/8" thickness of an appropriate CHAPCO® cementitious floor patch directly over the Defender EZ™ (no primer required). If thicker cementitious smoothing and leveling is needed, install a CHAPCO® self-leveling underlayment directly over the Defender EZ™ (no primer required). If the concrete surface is smooth and level enough to accept vinyl flooring, a minimum 1/8" thickness of CHAPCO® cementitious floor patch must still be installed over Defender EZ™ prior to application of the RollFast™ Vinyl Flooring Adhesive.

Alkalinity Test: Depending on flooring manufacturer's guidelines, a pH range of 7-11 is satisfactory for this adhesive. A reading outside of that range requires corrective measures before flooring installation. Always follow flooring manufacturer's guidelines for acceptable levels of alkalinity for the vinyl flooring.

Porosity Test: Surface porosity must be determined prior to application of adhesive and installation of flooring products. To test porosity, place a few drops of water on the substrate surface in several places; if the water is absorbed into the surface in less than 10 seconds, an application of CHAPCO® MP Multi-Purpose Primer is mandatory before the application of adhesive because the substrate is very porous. Follow PDS instructions for the primer application, then follow the specific adhesive installation instructions listed below.

Application Instructions

1. Thoroughly read installation instructions on this Product Data Sheet (PDS), read the Safety Data Sheet (SDS), and read vinyl flooring manufacturer instructions regarding conditioning the vinyl flooring, prior to installation.
2. Substrate must be clean, dry, and free of dust, grease, paints, oils, or any other foreign material. Existing adhesive must be removed by mechanical means, such as shot blasting or scarification. Do not use solvents or liquid adhesive removers. Cracks and uneven surfaces must be filled with a suitable CHAPCO® cement-based floor patch and/or underlayment.
3. No mixing required, just pour to use.
4. As an option, when installing flooring where finished baseboards, door casings, cabinets or other "obstacles" are already in place, apply this adhesive adjacent to these types of finished areas first, using a deck paint pad applicator, as described in Steps 5 through 7 below. For application in areas where finishes are not yet in place, you can opt to skip directly to Step 8.
5. (Optional-see Step 4 above) Pour out a small pool of adhesive (approximately 6" to 9" in diameter) and use it to saturate the deck paint pad applicator.
6. Pour a continuous 1" (25 mm) wide bead of adhesive 1" to 3" (25-76 mm) away from any finished wall or "obstacle".
7. Spread the bead of adhesive up to the finished wall or "obstacle" using the saturated deck paint pad applicator, similar to a painting "cut in" procedure around areas that are not to be painted.

8. For application in an open floor area, use a 1/4" (6mm) nap paint roller. A 3/8" (9mm) nap roller may be required for stiffer, heavier vinyl flooring. Before applying this adhesive, separately pour out enough adhesive to fully saturate the roller; saturate the roller by rolling through this small pool of adhesive.
9. Pour an initial continuous 1" (25 mm) wide bead of adhesive onto the substrate, approximately 12" (30 cm) from any wall or barrier. Then pour additional 1" (25 mm) wide bead lines of adhesive across the subfloor area every 30" (76 cm)—only pour out enough bead lines for an area that you expect to roll out in 15 minutes.
10. Spread a continuous single coat of the adhesive over the substrate using the saturated roller, by running the roller side to side through each continuous adhesive bead, 15" (37 cm) to each side of the poured bead. Keep the roller saturated throughout the adhesive application.
11. After application of the adhesive, vinyl flooring installation can begin when the adhesive becomes clear and does not transfer to fingertips when lightly touched (10-15 minutes under normal conditions). Refer to vinyl flooring manufacturer's instructions, to install the flooring.
12. Once the vinyl flooring is installed, it must be rolled in both directions with a minimum of a 100 pound three-section roller. Use a small hand roller in areas that cannot be reached with a large roller. Foot traffic is acceptable immediately after rolling is completed.
13. Heat welding may be performed after 60 minutes.

Clean-up

Easy clean-up. Remove wet adhesive with a damp cloth. Remove dried adhesive using a cloth dampened with denatured alcohol.

6. AVAILABILITY AND COST

To locate a distributor in your area, please contact:

phone: 800-832-9002

website: chapco-adhesive.com

7. WARRANTY

H.B. Fuller Construction Products Inc. offers a limited warranty on this product when installed in accordance with H.B. Fuller Construction Products Inc. printed specifications. Ask your sales associate or call 800-832-9002 for a copy of the limited warranty.

8. MAINTENANCE

Not applicable.

9. TECHNICAL ASSISTANCE

Information is available by calling the Technical Support Hotline:

Toll-free: 800-832-9023

Fax: 630-952-1235

Technical and Safety Literature:

To acquire Technical and safety literature, please call 800-832-9023 or visit chapco-adhesive.com.