



CHAPCO® 752

Premium Transitional Vinyl Adhesive

PRODUCT DATA

1. PRODUCT NAME

CHAPCO® 752 Premium Transitional Vinyl Adhesive



2. MANUFACTURER

H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504-6451 U.S.A.
800.552.6225 Office
800-832-9023 Technical Support
800.952.2368 Fax
chapco-adhesive.com

3. DESCRIPTION

CHAPCO® 752 Premium Transitional Vinyl Adhesive is a solvent free, acrylic latex adhesive, with an aggressive initial tack, formulated for the installation of LVT plank and fiberglass back sheetgoods. This high strength adhesive is made for installations over porous and non-porous substrates. CHAPCO® 752 adhesive is CRI Green Label Plus certified, is SCAQMD 1168 compliant and contributes to LEED®.

Product Features

- Ideal for LVT, plank and fiberglass back sheetgoods
- Extended open time
- Excellent resistance to moisture and plasterizer migration
- Solvent free
- LEED® Compliant (VOC 0 g/L) and CRI Green Label Plus Certified

Packaging

Four U.S. Gallon pail (15.14 L)
Product #15035534

Coverage

Determine recommended trowel size based on flooring type. Coverage will vary with the absorption of substrate and trowel size. Figures below are presented only as guidelines.

Flooring Type	Recommended Trowel Size	Approximate Coverage
Porous substrate	1/16" x 1/16" x 1/16" (1.6 x 1.6 x 1.6 mm) V-notch trowel	150-175 sq. ft./gal. (14-16 m ² /3.78 L)
Non-porous substrate	1/32" x 1/16" x 1/32" (0.8 x 1. x 0.8 mm) Fine notch trowel	250-300 sq. ft./gal. (23-28 m ² /3.78 L)

Storage/Shelf Life

Protect adhesive from freezing. Maximum of 1 year from date of manufacture in unopened container.

Limitations

- All traffic must be restricted for 24 hours after installation. No heavy traffic, rolling loads or furniture placement for 72 hours after installation.
- Do not use when ambient or surface temperatures are below 60°F.
- Interior use only.
- The dimensional stability of some vinyl flooring products is very sensitive to fluctuations in ambient environment conditions. H.B. Fuller Construction Products Inc. is not responsible for installation issues caused by dimensional changes in flooring.

Cautions

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about guidelines

for the proper use and application of the covered CHAPCO® products under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

CHAPCO® 752 Premium Transitional Vinyl Adhesive	
Base	Acrylic latex
Physical State	Thin paste
Color	Off white
Open Time	Up to 4 hours depending on substrate porosity.
Weight per Gallon	8.6 lbs./gallon
VOC/Liter of Material	0 grams (calculated)
Freeze/Thaw Stability	Stable for 3 cycles at 10°F.
Storage	Avoid prolonged or repeated freeze thaw cycles. If frozen, allow to return to room temperature slowly and stir before use.
Shelf Life	Maximum 1 year from date of manufacture in properly stored, unopened package.

5. INSTALLATION INSTRUCTIONS

Suitable Substrates

When properly prepared, suitable substrates include:

- Concrete (all grade levels)
- Underlayment grade plywood
- Hardboard

Preparation of Surfaces

Floor must be clean, smooth, dry, and free of any foreign matter that would interfere with a good bond. Fill all cracks and depressions with a suitable cement-based floor patch. Moisture Test: Moisture testing must be performed in accordance to ASTM F1869 with levels not to exceed 8 lbs./1000 sq. ft./24 hrs. (3.63 kg/93 m²/24 hrs) and/or ASTM F2170 with levels not to exceed 86%. NOTE: Readings above 5 lbs./1000 sq.ft./24 hrs. (2.26 kg/93 m²/24 hrs) or 80% RH must include newly poured slabs with a functional vapor barrier in place, with declining values. For concrete with greater moisture levels, treat the concrete with CHAPCO'S DEFENDER™ Moisture Vapor Barrier. See Product Data Sheet for details. Alkalinity Test: A pH range of 7-9 is satisfactory. A reading outside of that range requires corrective measures before flooring installation.

Application Instructions

1. Read installation instructions and MSDS thoroughly prior to installation.
2. Substrate must be clean, dry, and free of dust, grease, paints, oils, or any other foreign material. Existing adhesive must be removed. Do not use solvents or liquid adhesive removers. Cracks and uneven surfaces must be filled with a Portland cement based patching compound.
3. IMPORTANT: Surface porosity must be determined prior to application of adhesive and installation of flooring products. Place a few drops of water on the substrate surface in several locations, if the water is absorbed into the surface within 60 seconds, the surface is porous; if not, the surface is nonporous. If water droplets absorb into the surface in less than 10 seconds, an application of CHAPCO® Multi-Purpose Primer is mandatory before the application of adhesive. Follow the specific installation instructions listed below.
4. For proper trowel selection see trowel guide on this label.
5. For Porous and Non-Porous Substrates: Trowel the CHAPCO® 752 adhesive onto the substrate and allow it to remain open until it becomes tacky-to-the-touch where very little adhesive



transfers to your fingertips allowing some transfer to the back of the flooring. The adhesive should be ready for installation in approximately 20 to 40 minutes under normal HVAC conditions. Adhesive transfer to the flooring is critical for a successful installation. If there is no adhesive transfer, remove the adhesive and re-apply new adhesive. (All flooring should be installed within 2 hours of the adhesive reaching the tacky-to-touch state. Open-times may be extended up to 4 hours, when applied over non-porous substrates.) The open and working time will depend on the temperature and humidity of the jobsite. Once the floor is installed, it must be rolled immediately in both directions with a 100 pound three-section roller. Use a small hand roller in areas that cannot be reached with a large roller. Note: Immediately after spreading adhesive, saturate a short nap paint roller with CHAPCO® 752 adhesive and back-roll to avoid visible trowel mark telegraphing after installation.

6. Wait a minimum of 24 hours before heat welding.

Clean-up

Remove wet adhesive with damp cloth. Remove dried adhesive with a cloth dampened with denatured alcohol.

6. AVAILABILITY

To locate a distributor in your area, please contact:

phone: 800-832-9002

website: chapco-adhesive.com

7. LIMITED WARRANTY

The product(s) covered by this Product Data Sheet are sold subject to a Limited Warranty and related terms. **H.B. Fuller Construction Products disclaims the implied warranties of merchantability and fitness for a particular purpose and all incidental and consequential damages arising out of the sale, purchase or use of this product.** For Limited Warranty details visit chapco-adhesive.com. To obtain a hard copy of the Limited Warranty call H.B. Fuller Construction Products at 800-832-9023 or mail a written request to the address in Section 2 of this Product Data Sheet.

8. MAINTENANCE

Not applicable.

9. TECHNICAL SERVICES

Technical and Safety Literature:

To acquire Technical and safety literature, please visit our website at chapco-adhesive.com.



H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504
PH 800.832.9002
chapco-adhesive.com