



CHAPCO® TROWELFAST™

Vinyl Flooring Adhesive

PRODUCT DATA

1. PRODUCT NAME

CHAPCO® 778 TrowelFast™ Vinyl Flooring Adhesive



2. MANUFACTURER

H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504-6451 U.S.A.
800.552.6225 Office
800.952.2368 Fax
chapco-adhesive.com

3. DESCRIPTION

CHAPCO® TrowelFast™ Vinyl Flooring Adhesive allows for the ease of use throughout the flooring installation process, fast and efficiently. This breakthrough, user-friendly adhesive is ideal for vinyl tile, vinyl plank, vinyl composition tile and solid vinyl sheetgoods. Ideal for heavy rolling loads (hospital beds, furniture, etc.). This unique formulation dries quickly, has excellent resistance to moisture and alkali, provides a long open time, is easy to clean up, and exhibits low-odor.

Product Features

- Ideal for LVT, LVP, VCT, and solid vinyl heterogeneous or homogeneous sheetgoods
- Underlayments including reground rubber and cork
- Resists adhesive displacement and disbonding under heavy rolling loads (hospital beds, furniture, etc.)
- Fast drying; accepts flooring as soon as 10-20 minutes
- Extended open time allows flooring installation for up to 6-8 hours
- Heat weld as soon as 60 minutes
- Moisture resistant up to 95% RH / 10 lbs. MVER*
- Solvent free and low VOC (VOC <1 g/L)
- LEED® Compliant and CRI Green Label Plus Certified

*Over newly poured concrete, with declining moisture values, and an intact vapor barrier beneath the slab.

Packaging

3.5 U.S. Gallon plastic pail (13.25 L)
Product #7200901269

Coverage

Determine recommended trowel size based on the flooring type. Figures below are presented only as guidelines.

General Flooring Types	Recommended Trowel Size	Approximate Coverage
Standard Vinyl Flooring	1/16" x 1/32" x 5/64" U-Notch Trowel	270-290 ft ² /US Gallon (25-27 m ² /3.78 L)
Stiff Heavy Vinyl Flooring	1/16" x 1/32" x 1/32" U-Notch Trowel	225-250 ft ² /US Gallon (21-23.2 m ² /3.78 L)
Integrated Cushion Back	1/16" x 1/16" x 1/16" Square-Notch Trowel	190-220 ft ² /US Gallon (17.7-20.4 m ² /3.78 L)

Storage/Shelf Life

Store at a moderate room temperature. Protect adhesive from freezing. Refer to the Technical Data section of this Product Data Sheet (PDS), for more information. Maximum of 1 year from date of manufacture in unopened container.

Limitations

- Although adhesive may be used when ambient or surface temperatures are between 60°F-90°F (16°C-32°C), always follow flooring manufacturer's temperature, acclimation and installation guidelines for the vinyl flooring being installed.
- Always protect newly-installed vinyl flooring from heavy traffic, rolling loads, appliance or furniture placement for 24 hours after flooring installation.
- Do not use with fiberglass-backed vinyl sheetgoods, nor directly over peel and stick tile.

- Not recommended for use with felt-backed or mineral-backed vinyl sheetgoods, linoleum or rubber.
- Not for use in areas subject to flooding or water immersion.
- Do not use in coolers, freezers or seasonally used buildings subject to temperature or humidity extremes.
- Not recommended for use on stairs or vertical surfaces.
- May be used over in-floor heating systems, with a maximum floor temperature of 85°F, if allowed by the flooring manufacturer.
- Not for exterior use. Interior use only.

Cautions

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about guidelines for the proper use and application of the covered CHAPCO® brand products under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

CHAPCO® TrowelFast™ Vinyl Flooring Adhesive 778	
Base	Polymer latex
Physical State	Medium paste
Color	Off white
Open Time	6-8 hours depending on substrate porosity.
Weight per Gallon	8.7 lbs./gallon
VOC/Liter of Material	<1 gram (calculated)
Freeze/Thaw Stability	Stable for 3 cycles at 10°F (-12°C).
Storage	For optimal shelf life, store at a moderate room temperature, in closed containers, and protect this adhesive from freezing. If frozen, allow to return to room temperature slowly and stir before use. Avoid prolonged or repeated freeze thaw cycles.
Shelf Life	Maximum of 1 year from date of manufacture, in unopened container.

5. INSTALLATION INSTRUCTIONS

Suitable Substrates

When properly prepared, suitable substrates include:

- Concrete (all grade levels)
- Underlayment grade plywood
- Gypsum substrates (properly prepared)
- Well bonded, smooth, wax-free, existing single layer non-cushioned resilient flooring

Preparation of Surfaces

Floor must be clean, smooth, dry, and free of any foreign matter that would interfere with a good bond. Existing adhesive must be removed by mechanical means, such as shot blasting or scarification. Be sure to use proper safety equipment for hazardous materials as old cutback adhesive may contain asbestos. Harmful dust may result. Inhalation of asbestos dust may cause asbestosis or other serious bodily harm. Consult all applicable government agencies for rules and regulations concerning the removal of floorings and adhesives that contain asbestos. Do not use solvents or liquid adhesive removers. Fill all cracks and depressions with a suitable CHAPCO® cement-based floor patch and/ or underlayment. Best practices for cleaning typically include vacuuming and damp mopping.



Moisture Test: Concrete moisture testing must be performed in accordance with ASTM F2170 with levels not to exceed 95% and/ or ASTM F1869 with levels not to exceed 10 lbs./1000 ft²/24 hrs. (4.54 kg/93 m²/24 hrs.) for newly poured concrete, with declining moisture values, and an intact vapor barrier beneath the slab.

For concrete with a prior history of uncorrected moisture conditions or problems involving higher moisture levels, treat the concrete with one of the following CHAPCO® brand moisture mitigation solutions:

CHAPCO'S DEFENDER™ - apply per PDS instructions and allow to cure. Once cured, apply CHAPCO® MP Multi-Purpose Primer followed by application of a minimum 1/8" thickness of the appropriate CHAPCO® cementitious floor patch. If thicker cementitious smoothing and leveling is needed, install a CHAPCO® self-leveling underlayment over the primed CHAPCO'S DEFENDER™. If the concrete is smooth and level enough to accept vinyl flooring and does not require a cementitious underlayment, TrowelFast™ Vinyl Flooring Adhesive may be applied directly to the cured CHAPCO'S DEFENDER™ surface.

CHAPCO® DEFENDER EZ™ - apply per PDS instructions and allow to dry. Apply a minimum 1/8" thickness of an appropriate CHAPCO® cementitious floor patch directly over the DEFENDER EZ™ (no primer required). If thicker cementitious smoothing and leveling is needed, install a CHAPCO® self-leveling underlayment directly over the DEFENDER EZ™ (no primer required). If the concrete surface is smooth and level enough to accept vinyl flooring, a minimum 1/8" thickness of CHAPCO® cementitious floor patch must still be installed over DEFENDER EZ™ prior to application of the TrowelFast™ Vinyl Flooring Adhesive.

Alkalinity Test: Concrete alkalinity testing must be performed in accordance with ASTM F710. A pH range of 7-11 is satisfactory for this adhesive. Confirm the acceptable range for the flooring per the manufacturer's guidelines. A reading outside of either range requires corrective measures before flooring installation. Always follow flooring manufacturer's guidelines for acceptable levels of alkalinity for the vinyl flooring.

Porosity Test: Substrate porosity testing must be performed in accordance with ASTM F3191. First prepare the substrate to a clean, sound condition, free of any matter that would interfere with a good bond. To test porosity, place a drop of water on the substrate surface in several places; if the water is absorbed into the surface in less than 10 seconds, an application of CHAPCO® MP Multi-Purpose Primer is mandatory before the application of adhesive because the substrate is very porous. Follow PDS instructions for the primer dilution and application, then follow the specific adhesive installation instructions listed below.

Application Instructions

1. Thoroughly read installation instructions on this Product Data Sheet (PDS), read the Safety Data Sheet (SDS), and read vinyl flooring manufacturer instructions regarding conditioning the vinyl flooring, prior to installation.
2. Substrate must be clean, dry, and free of dust, grease, paints, oils, or any other foreign material. Refer to complete instructions in Substrate Preparation section noted above.
3. Apply adhesive with appropriate trowel.
4. After application of the adhesive, vinyl flooring installation can begin when the adhesive becomes clear and does not transfer to fingertips when lightly touched (10-20 minutes under normal conditions). The open time to accept flooring is 6-8 hours. Once the vinyl flooring is installed, it must be rolled in both directions with a 100-150 pound three-section roller. Use a small hand roller in hard to reach areas.
5. Foot traffic is acceptable immediately after rolling the entire installation.
6. Rolling loads, appliance or furniture placement for 24 hours after flooring installation.
7. Heat welding may be performed as soon as 60 minutes.

Clean-up

Easy clean-up. Remove wet adhesive with a damp cloth. Remove dried adhesive using a cloth dampened with denatured alcohol.

6. AVAILABILITY AND COST

To locate a distributor in your area, please contact:

phone: 800-832-9002

website: chapco-adhesive.com

7. WARRANTY

H.B. Fuller Construction Products Inc. offers a limited warranty on this product when installed in accordance with H.B. Fuller Construction Products Inc. printed specifications. Ask your sales associate or call 800-832-9002 for a copy of the limited warranty.

8. MAINTENANCE

Not applicable.

9. TECHNICAL ASSISTANCE

Information is available by calling the Technical Support Hotline:

Toll-free: 800-832-9023

Fax: 630-952-1235

Technical and Safety Literature:

To acquire Technical and safety literature, please call 800-832-9023 or visit chapco-adhesive.com.



H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504
PH 800.832.9002
chapco-adhesive.com